



1s White PET 1s Silver Board

This cardboard features high-quality rigidity and smoothness. The Metalized Silver PET and Offset PET film coatings enhance the surface of the cardboard, providing a more elegant appearance. In both hot and cold environments, the film coating prevents undesirable creasing. It is particularly preferred in the Party Decorations, Pastry, and Bakery sectors.

Gramaj	Kalınlık	B stiffness	E stiffness
ISO 536	ISO 534	ISO 5628	ISO 5628
gr/m ²	mm	mNm	mNm
595	0.8	90	55
635	1.0	135	70
775	1.2	142	84
1020	1.5	209	137
1300	1.8	250	141
1405	2.0	451	256
1515	2.2	507	358
1650	2.5	589	447
1860	2.8	754	531
1960	3.0	835	689



Test	Tolerance	Test metod
Whitness	9.0% abs. %±5	ISO 287
Density	± 1,43	Türkoğlu
Humidity	9.0% abs. %±5	ISO 287
Thickness	± 0.5 mm Plate	ISO 534
Size	Plate ±0.5mm	Türkoğlu
Grammage	±0.5 %	ISO 536
Recyclability	1.00 ~ 3.00mm. % 97	FSC

Applications

> Extra-strong, rigid solid board, perfect for food packaging, pastry, trays, luxury packaging, weddings, birthday parties, bakeries, and other commercial uses, as well as Christmas and holiday celebrations, bakery sales, and much more.

Services

- > Embossing
- > Die Cutting
- > Guillotine Cutting
- > Strapping & Packaging
- > Labeling & Barcoding

Size

- > The smallest size 350 x 400mm
- > The largest size 1500 x 1800 mm

Applicable Printing

- > Serigraf
- > Dijital print

Description

- > Due to changes in raw materials, the values provided in the table may vary by ±7%.
- > The geometric mean stiffness value is provided and has been calculated using the formula: $\sqrt{(B \text{ Stiffness} * E \text{ Stiffness})}$.
- > For detailed inquiries and technical information, please contact our team.

Certificates



TR-34-K-124589



ISO 9001:2015



ISO 2200:2005
ISO 14001:2015

