



1s Gold PET 1s Liner CakeBoard

One side is coated with Gold metallized PET and other side is laminated with Liner paper. It offers the highest quality in terms of hardness and flatness. Cake boards are made of a material that is not easily torn, faded, or broken on the surface. The outer surface prevents oil and water absorption, and the product is resistant to moisture.

Grammage	Thickness	MD Stiffness	CD Stiffness
ISO 536	ISO 534	ISO 5628	ISO 5628
gr/m ²	mm	mNm	mNm
675	0.8	110	56
730	1.0	141	75
870	1.2	184	92
1095	1.5	300	162
1305	1.8	319	238
1375	2.0	546	315
1445	2.2	605	440
1725	2.5	686	528
1870	2.8	840	670
2100	3.0	982	783



Cutting Method	Std. Package	Std. Package
Flat Mold	Unit	Unit
Shape	Piece	Kg
Straight cut-With Handle-Flower cut	25-50-100-250	5 - 10
Straight cut-With Handle-Flower cut	25-50-100-250	5 - 10
Straight cut-With Handle-Flower cut	25-50-100	5 - 10
Straight cut-With Handle-Flower cut	10-25-50	5 - 10
Optional	Optional	Optional

Applications

- > Extra strong rigid boards for weddings, birthday parties, bakeries, and other commercial uses, as well as Christmas and holiday celebrations, bake sales, and more. The product is fingerprint-resistant, prevents scratches, and helps keep the cake stable.

Servises

- > Embossing
- > Die Cutting
- > Guillotine Cutting
- > Strapping & Packaging
- > Labeling & Barcoding

Size

- > The minimum 6 Ø
- > The maximum 40 Ø
- > Optional

Applicable Printing

- > Flexsograph
- > pattern printing
- > Digital printing

Description

- > Considering the variety of the raw materials, the values provided in the tables may vary by ±5%.
- > The stiffness Geometric Mean has been calculated using the formula $\sqrt{(B \text{ Stiffness} * E \text{ Stiffness})}$.
- > For detailed inquiries and technical information, please contact our team.

Certificates



TR-34-K-124589



ISO 9001:2015



ISO 2200:2005
ISO 14001:2015

